



29722

This home has been professionally insulated with

Owens Corning

PROPINK® L77 PINK Fiberglas™ Unbonded Loosefill Insulation

(Job Site Address)

Name Baron Sique Const.
Address 2153 Old Wire Rd
City Lake City State FL Zip _____

Owens Corning PROPINK® L77 PINK Fiberglas™ Unbonded Loosefill Insulation

Owens Corning will accept no responsibility when the product is not installed in accordance with the product label. Stated R-value is provided by installing the required number of bags at a thickness not less than the labeled minimum thickness. Installation of the required number of bags may yield more than the specified minimum thickness. Failure by the installer to provide both the required bags and at least the minimum thickness will result in lower insulation R-value.

Specification for Open Blow AtticsNew Construction ☒ Retrofit ☐

Number of bags used

22

Estimated R-value of previous insulation

Ø

Area of coverage (sq. ft.)

1458

Other type(s) of insulation in attic

Ø

Thickness of insulation

10 3/4

Depth of previous insulation

Ø

Attics

R-value	Bags Per 1000 Sq. Ft.	Maximum Net Coverage	Minimum Weight Sq. Ft.	Minimum Thickness (in)	Minimum Settled Thickness
R-13	9.5	80.9	0.80	4.75	4.75
R-19	14.1	121.2	0.868	6.75	6.75
R-23	17.4	152.3	0.91	7.75	7.75
R-25	19.2	166.8	0.968	9.00	9.00
R-30	23.0	207.6	0.928	10.25	10.25
R-38	29.6	295.5	0.953	12.75	12.75
R-44	35.1	358.8	0.982	14.75	14.75
R-49	39.6	407.2	0.997	16.25	16.25
R-60	48.5	511.1	0.998	19.50	19.50

Walls

R-value	Minimum Thickness	Installed Density Lbs. Per Cu. Ft.	Maximum Coverage Per Bag	Bags Per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
13	3.5 (2x4)	1.3	87.0	1.5	0.379
15	3.5 (2x4)	1.5	75.4	1.3	0.438
21	5.5 (2x6)	1.3	53.4	1.6	0.596
24	5.5 (2x6)	1.8	40.0	2.0	0.823

Floors

R-value	Minimum Thickness	Installed Density Lbs. Per Cu. Ft.	Maximum Coverage Per Bag	Bags Per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
31	2x8	1.4	39.0	2.6	0.846
35	2x10	1.4	32.6	2.7	1.079
48	2x12	1.5	23.5	4.2	1.406

Cathedral Ceiling

R-value	Minimum Thickness	Installed Density Lbs. Per Cu. Ft.	Maximum Coverage Per Bag	Bags Per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
28	2x8	1.3	42.0	3.3	0.785
38	2x10	1.3	32.8	4.4	1.000
44	2x12	1.3	27.1	5.9	1.219

This product shows negligible settling.

Loosefill insulations vary in thermal performance due to factors such as aging, mean temperature, settlement, convection, moisture absorption and installation variation. Convection in glass loosefill insulation installed in open attics can reduce its thermal performance in extreme winter temperatures during the heating season.

Contractor Moran Insulation Date 2/27/12 Builder _____ Date _____
Company S. Moran (Signature) Company _____ (Signature)
Address _____ Address _____
Phone _____ Phone _____



OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO, USA 43659
1-800-GET-PINK®
www.owenscorning.com

Pub. No. 45145-E Printed in U.S.A. January 2010.
The color PINK is a registered trademark of Owens Corning. ©2010 Owens Corning.